



W A X



WAX WITH AN OPAQUE OR SEMI GLOSSY EFFECT, FOR THE PROTECTIVE FINISH OF THE MATÈRIKA LINE

Final average consumption

on MATÈRIKA 0,180 l/m²

on MATÈRIKA LIGHT 0,080 l/m²

on MATÈRIKA EXTRALIGHT 0,060 l/m²

on MATÈRIKA SOFT 0,060 l/m²

Packaging

1L • 5L

K WAX is a monocomponent metallic wax, with an opaque or semi glossy effect, whose high resistance composition allows excellent protection of decorative resin coatings made with the MATÈRIKA line, for which it was specially formulated

K WAX creates a protective coat against wear and tear for daily use, facilitating the cleaning and periodic maintenance of the surfaces on which it is applied.

Use

K WAX is used for the final protection of internal surfaces (walls and floors), of environments for civil use (homes, hotels, show-rooms, shops, offices, etc...) decorated with resin coatings from the MATÈRIKA line, in the version with an opaque or semi glossy effect, depending on the desired effect.

Advantage

- High stain resistance
- Solvent free
- Easy application

How to use

Surface preparation

K WAX is applied on surfaces made with the MATÈRIKA line after a period of about 24 hours from the K FINISH or K FINISH MONO application. The support must be perfectly dry and clean.

Product preparation

K WAX is ready to use. Briefly shake the product inside the package before use

Application of the material

Pour K WAX inside a clean container, in which to impregnate the spreader or a microfiber cloth, to distribute K WAX on the surface in two/three coats, each after drying the previous one.



Technical data

| PARAMETR | VALUE |
|------------------------------------|---|
| Product constituent | monocomponent |
| Appearance | white liquid |
| Gloss 60° (smooth support) | opaque 18 ± 2 GU |
| | semi glossy 51 ± 2 GU |
| PH | 8,4 ± 0,2 |
| Specific weight | 1,036 g/l |
| Dry substance | 25% |
| Active substance | 29% |
| Friction coefficient (ASTM2047/75) | 0,56 |
| Solubility in water | soluble |
| Flammability | not inflammable |
| Drying time | approx. 30-45 min. |
| Overlapping | approx. 60 min. |
| Min. Temp. Application | + 5 °C |
| Final average consumption | on MATÈRIKA 0,180 l/m ² |
| | on MATÈRIKA LIGHT 0,080 l/m ² |
| | on MATÈRIKA EXTRALIGHT 0,060 l/m ² |
| | on MATÈRIKA SOFT 0,060 l/m ² |
| Storage | 12 months at temperature between + 5° and +35°C |



K Finish



K Wax

Packaging

1 - 5

Warnings

Do not apply inside showers or bathtubs. It fears frost. Do not apply at a temperatures below +5 °c. Store in a dry place at a temperature of +5°C to + 35°C. Irritating to the eyes. In case of contact wash thoroughly with water and if necessary consult a doctor. Use latex gloves. Store out of the reach of children. Do not disperse the container in the environment after use. Always check the latest updated version of the technical sheet (resinamaterica.com).

Specification

Final protection of internal surfaces (walls and floors) of civil environments (homes, shops, showrooms, hotels, etc.) decorated with resin coatings of the MATÈRIKA line (already treated with K FINISH or K FINISH MONO), creating a protective coat to wear, by two/ three applications, for an average final consumption of about 0.180 lt/m² ON MATÈRIKA, 0.080 lt/m² on MATÈRIKA LIGHT , 0.060 lt/m² on Matèrika Extraligh and Matèrika Soft.

